

Petrotex 8823

Carboxylate Styrene-Butadiene Emulsion Latex

Product data:

Property	Unit	Value
Solid Content	%	50 ± 1
Viscosity(Brookfield SP.2, rpm:12 at 20°C)	cP	500 ±100
pH(25 °C)		7.5 ± 1
Density	g/cm ³	1.02 ± 0.005
MFFT	°C	0
Surface Tension	(mN/m) at 25 °C	44 ± 5
Appearance		Milky White

Application:

- Secondary backing of tufted carpet

Advantages:

- Medium-Soft handle with good coverage of the carpet backing
- Excellent adhesion between two carpet layers
- Excellent filler acceptance and compound stability
- High resistance to water and moisture penetration
- Low VOC and odor

Storage:

- Storage temperature: 10 to 35 °C
- Protect from frost, direct sunlight, and extreme heat
- Keep container tightly closed after each use
- Stir before use

Shelf life:

- 8 months from the date of manufacture
- If stored properly, it can be used after 8 months, subject to passing a quality check

Packaging:

- It can be transported in metal drum or plastic drum, IBCs and flexi tank.