

Petrotex 8858

Carboxylate Styrene-Butadiene Emulsion Latex

Product data:

Property	Unit	Value
Solid Content	%	50 ± 1
Viscosity(Brookfield SP.4, rpm:12 at 20°C)	cP	6000 ± 1000
pH(25 °C)		7.5 ± 1
Density	g/cm ³	1.03 ± 0.005
MFFT	°C	65
Appearance		Milky White

Application:

- Automotive carpet and similar molded parts

Advantages:

- Provides enhanced stiffness and dimensional stability in molded carpet components
- High resistance to flame and heat
- Excellent mechanical stability during mixing and application
- High resistance to humidity and hydrolysis in automotive environments
- Low VOC and odor

Storage:

- Storage temperature: 10 to 35 °C
- Protect from frost, direct sunlight, and extreme heat
- Keep container tightly closed after each use
- Stir before use

Shelf life:

- 8 months from the date of manufacture
- If stored properly, it can be used after 8 months, subject to passing a quality check

Packaging:

- It can be transported in metal drum or plastic drum and IBCs