

Petrotex 8882-2

Carboxylate Styrene-Butadiene Emulsion Latex

Product data:

Property	Unit	Value
Solid Content	%	50 ± 1
Viscosity(Brookfield SP.2, rpm:12 at 20°C)	cP	500 ±150
pH (25°C)		7.5 ± 1
Density	g/cm ³	1.03 ± 0.005
MFFT	°C	0
Surface Tension	(mN/m) at 25 °C	47 ± 5
Appearance		Milky White

Application:

- Back coating for tufted carpet

Advantages:

- Soft and tough polymer for secondary backing of tufted carpet
- Excellent filler acceptance and compound stability
- Superior adhesion firmly secures tuft yarns to the secondary backing
- Good filled film with excellent thermal stability and heat-aging properties
- Low VOC and odor

Storage:

- Storage temperature: 10 to 35 °C
- Protect from frost, direct sunlight, and extreme heat
- Keep container tightly closed after each use
- Stir before use

Shelf life:

- 8 months from the date of manufacture
- If stored properly, it can be used after 8 months, subject to passing a quality check

Packaging:

- It can be transported in metal drum or plastic drum and IBC