

Petrotex 8885

Carboxylate Styrene-Butadiene Polymer Emulsion

Product data:

Property	Unit	Value
Solid Content	%	50 ± 1
Viscosity(Brookfield SP.2, rpm:12 at 20°C)	cP	500 ± 200
pH(25 °C)		7.5 ± 1
Density	g/cm ³	1.03 ± 0.005
MFFT	°C	38
Surface Tension	(mN/m) at 25 °C	40 ± 5
Appearance		Milky White

Application:

- Nonwoven Textiles
- needle-punched carpet

Advantages:

- Provides a firm hand with Excellent fiber adhesion
- Excellent filler acceptance and compound stability
- Suitable thermal Resistance for High Temperature Processing
- High viscosity stability with normal Acrylate thickener

Storage:

- Storage temperature: 5 to 35 °C
- Protect from frost, direct sunlight, and extreme heat
- Keep container tightly closed after each use
- Stir before use

Shelf life:

- 12 months from manufacturing
- If stored properly, it can be used after 12 months, subject to passing a quality check

Packaging:

- It can be transported in metal and plastic drum, IBC and flexi tank