

## Petrotex 8890

Carboxylate Styrene-Butadiene Emulsion Latex

### Product data:

Property	Unit	Value
Solid Content	%	50 ± 1
Viscosity(Brookfield SP.2, rpm:12 at 20°C)	cP	150 ±50
pH(25 °C)		7 ± 1
Density	g/cm <sup>3</sup>	1.04 ± 0.005
MFFT	°C	40
Surface Tension	(mN/m) at 25 °C	43 ± 5
Appearance		Milky White

### Application:

- Binding of non-woven fabrics

### Advantages:

- Creates a firm handle with excellent resistance to washing
- Excellent filler acceptance and compound stability
- High viscosity stability with normal Acrylate thickener
- Excellent resistance against water and moisture
- Low VOC and odor

### Storage:

- Storage temperature: 10 to 35 °C
- Protect from frost, direct sunlight, and extreme heat
- Keep container tightly closed after each use
- Stir before use

### Shelf life:

- 8 months from the date of manufacture
- If stored properly, it can be used after 8 months, subject to passing a quality check

### Packaging:

- It can be transported in metal drum or plastic drum, IBCs and flexi tank.