

# Petrotex 6040

Styrene-butadiene Emulsion Latex

## Product data:

Solid Content	%	45±1
Viscosity	cP	50 Max
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		8±1
Density	g/cm <sup>3</sup>	1.01±0.005
Surface Tension	(mN/m) at 25 °C	42±5
MFFT	°C	7
Appearance		Milky White

## Application :

Admix with concrete

## Advantage :

- Great increase in abrasion resistance
- Increase resistance to water penetration
- Excellent adhesion to concrete components and improvement of concrete mixing
- Keep the moisture of the cement mixture and increasing open -time

## Storage :

- It must be stored between 5- 40 °C. keep away from direct heat and sunlight.
- Avoid freezing.
- Keep containers closed when not in use.
- Mix prior to use.

## Shelf life :

- One year since manufacturing .
- It can be used after a year if the test result meets standard.

## Delivery :

- It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

[WWW.PETROTEXIRAN.COM](http://WWW.PETROTEXIRAN.COM)

Unit 5, No 9, Masumi St .North  
Sheikh Bahayi St. Mollasadra St.  
Tehran, IRAN

Postal Code : 1991834994

