

Petrotex 6040P

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

| | | |
|--------------------------------|-------------------|--------------|
| Solid Content | % | 46±1 |
| Viscosity | cP | 35±10 |
| Brookfield SP.2.12rpm at 20 °C | | |
| pH at (25 °C) | | 8.5±0.5 |
| Density | g/cm ³ | 1.0015±0.005 |
| Surface Tension | (mN/m) at 25 °C | 42±5 |
| MFFT | °C | 5 |
| Appearance | | Milky White |

Application:

Admix with concrete

Advantages:

Excellent adhesion to concrete components and improvement of concrete mixing

Increase resistance to water penetration

Great increase in compressive strength and abrasion resistance

Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

Shelf life:

One year since manufacturing.

It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North

Sheikh Bahayi St. Mollasadra St.

Tehran, IRAN

Postal Code : 1991834994

