

Petrotex 6675

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	50±1
Viscosity	cP	200-600
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		8±1
Density	g/cm ³	1.02±0.005
Surface Tension	(mN/m) at 25 °C	40±5
MFFT	°C	0
Appearance		Milky White

Application:

Production of all types of waterproofing, especially roof covering

Advantages:

High water resistance and provides excellent water ability
Improved bonding and adhesion to cementitious substrates
Provides flexible coating with good elongation
Highly resistance to alkaline hydrolysis
Excellent adhesion to construction materials
Excellent filler acceptance

Storage:

It must be stored between 5-40°C. keep away from direct heat and sunlight.
Avoid freezing.
Keep containers closed when not in use.
Mix prior to use.

Shelf life:

One year since manufacturing.
It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994