

Petrotex 8000

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

| | | |
|--------------------------------|-------------------|-------------|
| Solid Content | % | 50±1 |
| Viscosity | cP | 200±100 |
| Brookfield SP.2.12rpm at 20 °C | | |
| pH at (25 °C) | | 8±0.5 |
| Density | g/cm ³ | 1.03±0.005 |
| Surface Tension | (mN/m) at 25 °C | 42±5 |
| MFFT | °C | 0 |
| Appearance | | Milky White |

Application:

Finishing high density carpet

Advantages:

High penet ration to superior binding of warp and weft
Soft handle
Good filled film charecteristics
Excellent thermal stability
Good viscosity stability with acry late thickener

Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.
Avoid freezing.
Keep containers closed when not in use.
Mix prior to use.

Shelf life:

One year since manufacturing.
It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994

