

Petrotex 8020

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

| | | |
|--------------------------------|-------------------|-------------|
| Solid Content | % | 50±1 |
| Viscosity | cP | 300±100 |
| Brookfield SP.2.12rpm at 20 °C | | |
| pH at (25 °C) | | 6.5±0.5 |
| Density | g/cm ³ | 1.03±0.005 |
| Surface Tension | (mN/m) at 25 °C | 45±5 |
| MFFT | °C | 0 |
| Appearance | | Milky White |

Application:

Finishing machine carpet

Advantages:

- Soft handle
- Good filled film characteristics
- Excellent thermal stability
- Good water resistance and low water absorption

Storage:

- It must be stored between 5-40°C. keep a way from direct heat and sunlight.
- Avoid freezing.
- Keep containers closed when not in use.
- Mix prior to use.

Shelf life:

- One year since manufacturing.
- It can be used after a year if the test result meets standard.

Delivery:

- It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994

