

# Petrotex 8060

Carboxylated Styrene-butadiene Emulsion Latex

## Product data:

Solid Content	%	50±1
Viscosity	cP	800 ±200
Brookfield SP.2.12rpm at 20 °C		7.5 ± 1
pH at (25 °C)		
Density	g/cm <sup>3</sup>	1.02±0.005
MFFT	°C	0
Surface Tension	(mN/m) at 25 °C	45±5
Appearance		Milky White

## Application :

Coating metal surfaces

## Advantage :

High adhesion ability on metal surfaces  
Very low water absorption

## Storage :

It must be stored between 5- 40 °C. keep away from direct heat and sunlight.  
Avoid freezing.  
Keep containers closed when not in use.  
Mix prior to use.

## Shelf life :

One year since manufacturing .  
It can be used after a year if the test result meets standard.

## Delivery :

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

[WWW.PETROTEXIRAN.COM](http://WWW.PETROTEXIRAN.COM)

Unit 5, No 9, Masumi St. North  
Sheikh Bahayi St. Mollasadra St.  
Tehran, IRAN  
Postal Code : 1991834994

