

# Petrotex 8242

Carboxylated Styrene-butadiene Emulsion Latex

## Product data:

Solid Content	%	51±1
Viscosity	cP	1100±100
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		8±1
Density	g/cm <sup>3</sup>	1.02±0.005
Surface Tension	(mN/m) at 25 °C	44±5
MFFT	°C	0
Appearance		Milky White

## Application :

Finishing tufted carpet

## Advantages :

Soft handle  
Stable foam  
Excellent adhesion between  
Excellent lay-flat characteristics  
Good filler acceptance  
Good wet delamination strength with excellent thermal  
Good viscosity stability with acrylate thickeners

## Storage :

It must be stored between 5- 40 °C. keep away from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

## Shelf life :

One year since manufacturing .

It can be used after a year if the test result meets standard.

## Delivery :

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

[WWW.PETROTEXIRAN.COM](http://WWW.PETROTEXIRAN.COM)

Unit 5, No 9, Masumi St .North  
Sheikh Bahayi St.MollasadraSt.  
Tehran, IRAN  
Postal Code : 1991834994

