

Petrotex 8800

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	50±1
Viscosity	cP	300±100
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		8±1
Density	g/cm ³	1.03±0.005
Surface Tension	(mN/m) at 25 °C	45±5
MFFT	°C	0
Appearance		Milky White

Application :

Finishing tufted carpets and high density machine carpets

Advantages :

- Soft handle
- High penetration for superior of warp and weft
- Good filled film characteristics with excellent heat stability
- Excellent wet film stability with high tackiness
- Good viscosity stability with acrylate thickeners

Storage :

- It must be stored between 5- 40 °C. keep away from direct heat and sunlight.
- Avoid freezing.
- Keep containers closed when not in use.
- Mix prior to use.

Shelf life :

- One year since manufacturing .
- It can be used after a year if the test result meets standard.

Delivery :

- It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St .North
Sheikh Bahayi St.MollasadraSt.
Tehran, IRAN
Postal Code : 1991834994

