

Petrotex 8805

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	45±1
Viscosity	cP	50 Max
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		7.5±0.5
Density	g/cm ³	1.03±0.005
Surface Tension	(mN/m) at 25 °C	40±5
MFFT	°C	70
Appearance		Milky White

Application:

Non-woven textile

Advantages:

- Good filler acceptance and compound stability
- Very hard handle
- Ability to mix with powders and additives
- Good viscosity stability with acrylate thickeners

Storage:

- It must be stored between 5-40°C. keep a way from direct heat and sunlight.
- Avoid freezing.
- Keep containers closed when not in use.
- Mix prior to use.

Shelf life:

- One year since manufacturing.
- It can be used after a year if the test result meets standard.

Delivery:

- It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994

