

Petrotex 8810

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	50±1
Viscosity	cP	500±100
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		7.5±0.5
Density	g/cm ³	1.03±0.005
Surface Tension	(mN/m) at 25 °C	45±5
MFFT	°C	0
Appearance		Milky White

Application:

Finishing machine carpet

Advantages:

Soft handle
High penetration for superior binding of warp and weft
Good filled film characteristics with excellent heat stability
Good viscosity stability with acrylate thickeners

Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.
Avoid freezing.
Keep containers closed when not in use.
Mix prior to use.

Shelf life:

One year since manufacturing.
It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994

