

Petrotex 8814

Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	46±1
Viscosity	cP	50 MAx
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		8.5±0.5
Density	g/cm ³	1.01±0.005
Surface Tension	(mN/m) at 25 °C	42±5
MFFT	°C	5
Appearance		Milky White

Application:

Admix with concrete

Advantages:

Excellent adhesion to concrete components and improvement of concrete mixing

Great increase in compressive strength and abrasion resistance

Great increase resistance to water penetration

Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

Shelf life:

One year since manufacturing.

It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994

