

Petrotex 8822N

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	51±1
Viscosity	cP	150±50
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		7±0.5
Density	g/cm ³	1.03±0.05
Surface Tension	(mN/m) at 25 °C	40±5
MFFT	°C	0
Appearance		Milky White

Application :

Finishing tufted carpet

Advantages :

Soft handle
Stable foam
Excellent adhesion layers
Good wet delamination strength
Excellent lay-flat characteristics
Good wet delamination strength with excellent thermal stability
Good viscosity stability with acrylate thickeners

Storage :

It must be stored between 5- 40 °C. keep away from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

Shelf life :

One year since manufacturing .

It can be used after a year if the test result meets standard.

Delivery :

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN

Postal Code : 1991834994

