

# Petrotex 8840

Carboxylated Styrene-butadiene Emulsion Latex

## Product data:

Solid Content	%	50±1
Viscosity	cP	700±200
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		7.5±0.5
Density	g/cm <sup>3</sup>	1.03±0.005
Surface Tension	(mN/m) at 25 °C	42±5
MFFT	°C	8
Appearance		Milky White

## Application :

Finishing of medium density machine carpet

## Advantages :

Normal handle with very low foam

High penetration for superior binding of warp and weft with excellent thermal stability

Excellent water resistance and low water absorption

Good viscosity stability with acrylate thickeners

## Storage :

It must be stored between 5- 40 °C. keep away from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

## Shelf life :

One year since manufacturing .

It can be used after a year if the test result meets standard.

## Delivery :

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

[WWW.PETROTEXIRAN.COM](http://WWW.PETROTEXIRAN.COM)

Unit 5, No 9, Masumi St. North  
Sheikh Bahayi St. Mollasadra St.

Tehran, IRAN

Postal Code : 1991834994

