

Petrotex 8858

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	50±1
Viscosity	cP	6000±1000
Brookfield SP.4.12rpm at 20 °C		
pH at (25 °C)		8±1
MFFT	°C	65
Appearance		Milky White

Application :

Car carpet

Advantages :

Excellent formability- dimensional stability
Tough and stiff handle
Excellent resistance to burning
Creates a great bond with fibers

Storage :

It must be stored between 5- 40 °C. keep away from direct heat and sunlight.
Avoid freezing.
Keep containers closed when not in use.
Mix prior to use.

Shelf life :

One year since manufacturing .
It can be used after a year if the test result meets standard.

Delivery :

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St .North
Sheikh Bahayi St.MollasadraSt.
Tehran, IRAN
Postal Code : 1991834994

