

# Petrotex 8866

Carboxylated Styrene-butadiene Emulsion Latex

## Product data:

Solid Content	%	50±1
Viscosity	cP	150±100
Brookfield SP.2.12rpm at 20 °C		
pH at (25 °C)		7.5±0.5
Density	g/cm <sup>3</sup>	1.03±0.005
Surface Tension	(mN/m) at 25 °C	40±5
MFFT	°C	23
Appearance		Milky White

## Application:

Felt carpets

## Advantages:

Excellent filler acceptance  
Provides excellent bonding and stiff handle  
The viscosity can be adjusted by thickeners  
Excellent heat stability

## Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.  
Avoid freezing.  
Keep containers closed when not in use.  
Mix prior to use.

## Shelf life:

One year since manufacturing.  
It can be used after a year if the test result meets standard.

## Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

[WWW.PETROTEXIRAN.COM](http://WWW.PETROTEXIRAN.COM)

Unit 5, No 9, Masumi St. North  
Sheikh Bahayi St. Mollasadra St.  
Tehran, IRAN  
Postal Code : 1991834994

