

Petrotex 8880-H3

Carboxylated Styrene-butadiene Emulsion Latex

Product data:

Solid Content	%	50±1
Viscosity	cP	200 ±100
Brookfield SP.2.12rpm at 20 °C		7± 0.5
pH at (25 °C)		
Density	g/cm ³	1.02±0.005
MFFT	°C	16
Surface Tension	(mN/m) at 25 °C	45±5
Appearance		Milky White

Application :

Foam back coating felt carpets

Advantage :

Excellent mix ability
Excellent filler acceptance
Good washing resistance
High foam stability

Storage :

It must be stored between 5- 40 °C. keep away from direct heat and sunlight.
Avoid freezing.
Keep containers closed when not in use.
Mix prior to use.

Shelf life :

One year since manufacturing .
It can be used after a year if the test result meets standard.

Delivery :

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5, No 9, Masumi St. North
Sheikh Bahayi St. Mollasadra St.
Tehran, IRAN
Postal Code : 1991834994

