

# Petrotex V290

Ter-polymer of Vinyl Pyridine, Styrene and Butadiene Emulsion Latex

## Product data:

Solid Content	%	40±1
Viscosity	cP	60±10
Brookfield SP.2.12rpm at 20°C		
pH at (25°C)		11±1
Surface Tension	°C	50±5
Bound VP		10±1
Appearance		Light Purple

## Application:

Dipped Fabrics used for Carcass , conveyor belt ,and other textile reinforced rubberbased products. .

## Advantages:

It provides the excellent adhesion between dipped and calendered tyre cord fabric and the rubber compound

It is specially designed to provide a strong bond between synthetic tyre cord fabrics and the rubber compound.

## Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

## Shelf life:

One year since manufacturing.

It can be used after a year if the test result meets standard.

## Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

[WWW.PETROTEXIRAN.COM](http://WWW.PETROTEXIRAN.COM)

Unit 5, No 9, Masumi St. North

Sheikh Bahayi St. Mollasadra St.

Tehran, IRAN

Postal Code : 1991834994

