

Petrotex N300

Carboxylated Styrene-butadiene Emulsion Latex

Product data: ::

Solid Content % 44±1

Viscosity cP 100 Max

Brookfield SP.2.12rpm at 20 °C

pH at (25 °C) 8±1

Surface Tension (mN/m) at 25 °C 40±5

Appearance Milky White

Acrylonitrile content Medium

Antioxidant Yes

Application:

Examination thin gloves

Advantages:

Suitable for thin examiation gloves (<0.1mm)

Good high tensile strength and softness

Good resistance against chemicals and oils

Fast gelling for good productivity

Good compound stability

Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

Shelf life:

One year since manufacturing.

It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5,No 9, Masumi St.North Sheikh Bahayi St.MollasadraSt. Tehran, IRAN

Postal Code: 1991834994

9





