

Petrotex N380

Carboxylated Styrene-butadiene Emulsion Latex

| P | ro | dı | uc | t c | ak | ta: |
|---|---------------|----------|----|-----|----|-----|
| | $\overline{}$ | U | чν | | лч | · |

Solid Content % 44±1

Viscosity cP 100 Max

Brookfield SP.2.12rpm at 20 °C

pH at (25 °C) 8±1

Surface Tension (mN/m) at 25 °C 40±3

Appearance Milky White

Acrylonitrile content Medium

Antioxidant Yes

Application:

Unsupported industrial and household gloves

Advantages:

Good tensile strength and flexibility

High resistance against chemicals and oils

Excellent for making flock line industrial gloves

Fast gelling for good productivity

Good compound stability

Storage:

It must be stored between 5-40°C. keep a way from direct heat and sunlight.

Avoid freezing.

Keep containers closed when not in use.

Mix prior to use.

Shelf life:

One year since manufacturing.

It can be used after a year if the test result meets standard.

Delivery:

It can be transported in flexi tanks, IBCs and drums.

(+9821) 42 437

(+9821) 88 62 48 72

WWW.PETROTEXIRAN.COM

Unit 5,No 9, Masumi St .North Sheikh Bahayi St.MollasadraSt.

Tehran, IRAN

Postal Code: 1991834994









